



Your Tubular Product Specialists

SA-213-TP304H

Seamless ferritic and austenitic alloy steel boiler, superheater, and heat exchanger tubes.

Chemical Properties:

Carbon: 0.04-0.10 Silicon: 0.75 max.

Manganese: 2.00 Nickel: 8.00-11.0

Potassium: 0.04 Chromium: 18.0-20.0

Sulfur: 0.03 Molybdenum: n/a

Mechanical Properties:

Tensile Strength:

ksi: 75

MPa: 517

Yield:

ksi: 30

MPa: 207

Elongation in 2in. or 50mm, min. %: 35

Max. Hardness Rockwell B: 90